

## tec-speed 1.1 - VT-464(D)

UL Approval: E214381    Version: 4 /127 /128

### Laminate/Prepreg

## General Information

- > Halogen Free & Mid-Tg
- > Low Dk & Low Loss
- > Excellent Thermal Reliability
- > Lead Free Process Compatible
- > Ease of Manufacturing

## Application

High Frequency & High Speed, Satellite Communication, Navigation, GPS, LTE, Handhelds, etc

## Availability

- > Core Thickness: 0.002" (0.05mm) to 0.200" (5mm), available in sheet or panel form
- > Copper Foil: 1/4oz to 12oz
- > Prepregs are available in roll or panel form
- > E-Glass styles: 7628, 1506, 1500, 2113, 2313, 3313, 2116, 1080, 1086, 1078, 106 & 1067, etc
- > Ability of Processing Copper Type: HTE, RTF, VLP & HVLP

Properties		Prepreg		Laminate
Storage Condition	Temperature	Below 23 °C (73 °F)	Below 5 °C (41 °F)	Room
	Relative humidity	Below 55% RH	/	/
Shelf Life		3 months	6 months	24 months (airproof)

The prepreg exceeding shelf life should be retested.

#### CORPORATE HEADQUARTERS

**Ventec Electronics Co. Ltd.**  
308 TaiShan Rd,  
New District Suzhou,  
Jiangsu, P.R. China 215129  
T: +86 512-68091810  
Email: sales@ventec.com.cn

#### EMEA REGIONAL HEADQUARTERS

**Ventec Europe**  
Unit 1 Trojan Business Centre,  
Tachbrook Park Estate,  
Leamington-Spa, CV34 6RH, UK  
T: +44 1926-889822  
Email: sales@ventec-europe.com

#### AMERICAS REGIONAL HEADQUARTERS

**Ventec USA**  
21 Water Street, Amesbury,  
Massachusetts, MA 01913,  
United States of America  
T: +1 978-5219700  
Email: saleseast@ventec-usa.com

www.ventec laminates.com

## tec-speed 1.1 - VT-464(D)

UL Approval: E214381 Version: 4 /127 /128

### Laminate/Prepreg

## Properties Sheet IPC-4101E /127 /128

Properties		Test Method	Units	Specification	Typical Value
<b>Thermal Properties</b>					
Tg	DSC	IPC-TM-650 2.4.25	°C	150 minimum	160
	TMA	IPC-TM-650 2.4.24	°C	-	-
Td		ASTM D3850	°C	325 minimum	400
T260		IPC-TM-650 2.4.24.1	Minute	30 minimum	>60
T288		IPC-TM-650 2.4.24.1	Minute	5 minimum	>30
Thermal Stress @ 288°C		IPC-TM-650 2.4.13.1	Second	Pass 10s	>600
Z-axis CTE	Before Tg	IPC-TM-650 2.4.24	ppm/°C	60 maximum	70
	After Tg	IPC-TM-650 2.4.24	ppm/°C	300 maximum	280
	Total Expansion (50~260°C)	IPC-TM-650 2.4.24	%	3.5 maximum	3.2
MOT		UL 94	°C	-	130
<b>Electrical Properties</b>					
DK @ 1GHz	RC 50%	IPC-TM-650 2.5.5.9	-	5.4 maximum	3.6
	RC 75%				3.0
DF @ 1GHz	RC 50%	IPC-TM-650 2.5.5.9	-	0.035 minimum	0.006
	RC 75%				0.004
DK @ 10GHz	RC 53%	IPC-TM-650 2.5.5.13	-	-	3.4
DF @ 10GHz	RC 53%	IPC-TM-650 2.5.5.13	-	-	0.008
Volume Resistivity	After Moisture Resistance	IPC-TM-650 2.5.17.1	MΩ-cm	1.0E+4 minimum	5.0E+8
	E-24/125	IPC-TM-650 2.5.17.1	MΩ-cm	1.0E+3 minimum	5.0E+6
Surface Resistivity	After Moisture Resistance	IPC-TM-650 2.5.17.1	MΩ	1.0E+4 minimum	5.0E+7
	E-24/125	IPC-TM-650 2.5.17.1	MΩ	1.0E+3 minimum	5.0E+6
Electrical Strength		IPC-TM-650 2.5.6.2	Volt/mil (KV/mm)	762 (30) minimum	1372 (54)
Dielectric Breakdown		IPC-TM-650 2.5.6	KV	40 minimum	60
Comparative Tracking Index (CTI)		ASTM D3638	Rating (Volt)	-	Grade 3 (175~250)
Arc Resistance		ASTM D495	Second	60 minimum	195
<b>Mechanical Properties</b>					
Peel Strength (1oz)	As received	IPC-TM-650 2.4.8	lb/in (N/mm)	-	6.0 (1.05)
	After thermal stress	IPC-TM-650 2.4.8	lb/in (N/mm)	6.0 (1.05) minimum	6.0 (1.05)
Flexural Strength	Warp	IPC-TM-650 2.4.4	Kpsi (MPa)	60 (415) minimum	80 (560)
	Fill	IPC-TM-650 2.4.4	Kpsi (MPa)	50 (345) minimum	65 (450)
<b>Physical Properties</b>					
Moisture Absorption		IPC-TM-650 2.6.2.1	%	0.80 maximum	0.10
Flammability		UL-94	Rating	V0 minimum	V0

All test data provided are typical values and not intended to be specification values.

#### CORPORATE HEADQUARTERS

Ventec Electronics Co. Ltd.  
308 TaiShan Rd,  
New District Suzhou,  
Jiangsu, P.R. China 215129  
T: +86 512-68091810  
Email: sales@ventec.com.cn

#### EMEA REGIONAL HEADQUARTERS

Ventec Europe  
Unit 1 Trojan Business Centre,  
Tachbrook Park Estate,  
Leamington-Spa, CV34 6RH, UK  
T: +44 1926-889822  
Email: sales@ventec-europe.com

#### AMERICAS REGIONAL HEADQUARTERS

Ventec USA  
21 Water Street, Amesbury,  
Massachusetts, MA 01913,  
United States of America  
T: +1 978-5219700  
Email: saleseast@ventec-usa.com

www.ventec laminates.com